



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 1 059 361 A1

(12) EUROPEAN PATENT APPLICATION

(43) Date of publication:
13.12.2000 Bulletin 2000/50

(51) Int Cl.7: C22B 19/20, C22B 3/44,
C22B 15/00, C22B 23/00

(21) Application number: 00850095.1

(22) Date of filing: 30.05.2000

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(72) Inventor: Sundkvist, Jan-Eric
931 41 Skellefteå (SE)


(74) Representative: Lundin, Björn-Eric
Boliden Mineral AB,
Patent & Trade Marks,
P.O. Box 21024
100 31 Stockholm (SE)

(30) Priority: 06.06.1999 SE 9902008

(71) Applicant: Boliden Mineral AB
936 81 Boliden (SE)

(54) A method of purifying an iron-containing acid leaching solution

(57) A method of purifying an acid leaching solution obtained by processing hydrometallurgically material that contains valuable metals and also Fe^{3+} and Fe^{2+} , and possibly also arsenic in solution. The major part of the Fe^{3+} -content and the arsenic is precipitated out in a first stage, by adding pH-elevating agent to the leaching solution. The precipitate formed in the first precipitation stage is extracted from the solution and removed from the process. The solution is oxidised in a second precipitation stage while adding a further pH-elevating agent for oxidation of Fe^{2+} and precipitation of resultant Fe^{3+} and any arsenic still present. The resultant precipitate and any residual solid pH-elevating agent are then extracted from the solution and returned in the process to more acid conditions, and the thus purified solution is then processed to win its valuable metal content in a manner per se. The pH is suitably raised during the first stage to a value in the range of 2.2-2.8, and in the second stage to a value in the range of 3.0-4.5. The oxidising process in the second stage is suitably effected by injecting air into the solution and by preferably using lime or limestone as the pH-elevating agent. Solid material extracted from the second stage is returned beneficially to the first stage. Some of the solid material taken from each precipitation stage can be recycled within respective stages as a nucleating agent.



EP 1 059 361 A1

Description

[0001] The present invention relates to a method of purifying an acid leaching solution which has been obtained by hydrometallurgically working-up material that contains valuable metals, and that in addition to said valuable metals also includes Fe^{3+} and Fe^{2+} and possibly also arsenic in solution. Although the method can be used generally for acid leaching solutions of this nature regardless of the choice of hydrometallurgical process applied and the type of starting material, it is particularly suitable for purifying acid leaching solutions that result from bioleaching processes, i.e. processes in which bacteria are used to accelerate the leaching process.

[0002] Bioleaching is described generally in our earlier Patent Publications US-A-5,397,380 and SE-A-9901613-1, and, for instance, also in WO 9216667 which deals generally with the oxidation of metal sulphide material with thermo-tolerant bacteria and also in WO 94/28184 which relates to bioleaching of zinc concentrate.

[0003] It is necessary to cleanse leaching solutions of the kind described in the introduction of their iron and possible arsenic content, in order to be able to win their valuable metal contents economically, for instance their copper, zinc, nickel, cobalt and precious metal contents by electrowinning or by some other suitable process. In the known methods applied to this end, such acid solutions, which often have a pH of about 1, are neutralised with lime or some like pH-elevating agent so as to precipitate the iron, wherewith any arsenic present will also be precipitated at the same time. Total precipitation of the iron (III) content is obtained at pH 3.0-3.5. One such known method is described in AU-A-11201/92, for instance.

[0004] A relatively large percentage of the iron in a bioleaching solution is present in divalent form, Fe^{2+} , and it is necessary to convert all iron to a trivalent form, i.e. Fe^{3+} , by oxidation in order to be able to separate the iron from remaining metals (valuable metals) by precipitation. This is normally effected at a pH >3 by injecting air into the system so as to obtain a sufficiently rapid kinetic, in other words a high oxidation rate. However, when precipitating iron at such high pH values some precipitation of other metals will take place, caused by inclusions in the resultant voluminous iron hydroxide precipitate among other things, and consequently valuable metals will be lost in the precipitate to an extent which is economically significant with respect to most valuable metals.

[0005] Proposals have been made as to how the loss of valuable metals caused by this co-precipitation can be avoided or at least reduced. There is described in an article by A.P. Briggs et al (Int. Biohydrometallurgy Symposium IBS97, Sydney, 1997) a bacteria leaching process undertaken in Uganda to recover cobalt from roasted pyrites, in which the iron was precipitated incompletely in order to avoid cobalt losses. This process,

however, results in problems in the following cobalt recovery stage.

[0006] Another article by M.L. Steemson et al in the same publication (IBS97), there is described a bioleaching process for treating zinc concentrate, in which co-precipitation of zinc with the precipitation of iron is particularly upheld as a serious problem that necessitates re-dissolving the resultant iron precipitate and re-filtration in order to obtain a solution of the purity required for the subsequent zinc winning process using solvent extraction/electrowinning.

[0007] The object of the present invention is to greatly reduce the extent of the problems associated with the co-precipitation of valuable metal contents when purifying the aforescribed acid leaching solutions.

[0008] The inventive method is characterised to this end by the method steps set forth in the accompanying Claims. Thus, according to the present invention, the major part of the Fe^{3+} -content and arsenic content of the leaching solution is precipitated out in a first stage, by adding pH-elevating agent to the leaching solution. The precipitate formed in the first stage is separated from the solution and removed from the process. The precipitate-free solution is then oxidised in a second precipitation stage while adding additional pH-elevating agent to oxidise Fe^{2+} and therewith precipitate out the resultant Fe^{3+} and any arsenic that remains in the solution. The precipitate formed and any solid pH-elevating agent that remains is/are extracted from the solution and returned to the process to more acid conditions, and the thus purified, or cleansed, solution is then processed to recover its valuable metal content in a manner known per se. The pH is conveniently raised during the first process stage to a value lying in the range of 2.2-2.8, and is raised in the second process stage to a value lying in the range of 3.0-4.5. Oxidation in the second process stage is conveniently effected by injecting air into the solution. The pH-elevating agent may suitably be lime or limestone, although it will be understood that local conditions and possible access to other inexpensive and useful alkaline materials may be a deciding factor in this respect. All or part of the solid material extracted from the second process stage may conveniently be returned to the first process stage, therewith utilising the added alkaline material to a maximum. Part of the separated solid material obtained in each precipitation stage may be returned within respective stages as a nucleating agent. Thus, the only part of the precipitate obtained in the second process stage that is not returned to the first stage is the part which then circulates internally within said stage.

[0009] The invention will now be described in more detail with reference to the accompanying drawing, which has the form of a flowchart that illustrates a preferred embodiment of the method.

[0010] A sulphuric acid leaching solution containing iron, arsenic and also valuable metals that shall be won from the solution in later process stages is delivered to-

gether with lime to a reactor equipped with agitating or stirring means, or to a series of such reactors, for carrying out the first precipitation stage, which is effected by increasing the pH of the solution to a final value of 2.2-2.8. During this stage of the process, the major part of the trivalent iron present in the solution is precipitated together with any arsenic present. As much as 90-95% of the trivalent iron content and a significant part of the arsenic can be precipitated without risk of any co-precipitation of other metals. The resultant slurry is deslimed in a thickener, optionally with the aid of a flocculating additive. Because of the relatively low pH at which the precipitate obtained from the thickener was formed, the precipitate is dense, easily filtered and easily washed, and is washed with water and possibly also with an acid additive. A final iron-arsenic-gypsum precipitate free from valuable metal can be removed from the process and further filtered, including a number of washing stages or counterflow washing of the precipitate in a thickener or thickeners, and then transported to a waste dump. The washing liquid is suitably recovered and returned as leaching solution to the bioleaching stage. The overflow from the thickener downstream of the first precipitation stage will be relatively turbid if no flocculating agent has been added, since the overflow is led into the first reactor of a series of reactors in the second precipitation stage, together with lime or limestone.

[0011] The divalent iron present is oxidised in this second precipitation stage, by injecting air into the solution and raising its pH to a final value of about 3.0-4.5. As a result of this oxidation, practically all of the trivalent iron newly formed from the iron that remained after the first precipitation process is precipitated out together with any remaining arsenic. The precipitate obtained in the second precipitation stage is delivered to a thickener, suitably together with a flocculating agent, downstream of the last reactor in said second stage; the precipitate should really be referred to as a slurry in this stage of the process, because of its voluminous and fluffy physical consistency in a highly liquid environment. There is obtained from the thickener an iron-free and particle-free overflow of solution that contains valuable metals, which can be delivered to an appropriate metal winning process, for instance a liquid extraction process and following electrowinning process, without further treatment. The thickened slurry obtained in the second thickener and possibly containing co-precipitates of valuable metals in hydroxide form, is returned and fed into the first reactor in the first precipitation stage together with the acid leaching solution, where the conditions prevailing in the process are as acid as possible. All co-precipitates and any unreacted lime will be effectively dissolved in the more acid environment. As indicated, some of the thickened slurry obtained in the second thickener may be recycled to the second precipitation stage with the object of improving crystallisation in the precipitation process in this stage.

EXAMPLE

[0012] When purifying an acid leaching solution that had an initial pH of 1.5 and contained, *inter alia*, about 11.5 g/l iron and 4.8 g/l zinc in comparison trials using two-stage precipitation in accordance with the invention and conventional single-stage precipitation, it was established that the loss of Zn with the total precipitation of iron achieved by raising the pH to about 3 corresponded to about 35% of the total amount present. In the case of the two-stage precipitation process, it was surprisingly found that only negligible amounts of zinc were present in the precipitate, enabling the zinc loss to be set to 0 in practice.

[0013] The method according to the invention affords a number of advantages, some of which include

- minimum losses of valuable metals caused by co-precipitation (see the above example)
- minimum consumption of flocculating agent
- maximum appropriation of added alkali
- total precipitation of iron and arsenic is possible (in the absence of co-precipitation of other metals)
- iron/arsenic precipitates can be washed effectively by withdrawing the product from the circuit at low pH, and as a result of the low addition of flocculating agent.

Claims

1. A method of purifying an acid leaching solution obtained when working-up hydrometallurgically material that contains valuable metals, said solution also containing Fe^{3+} and Fe^{2+} and possibly also arsenic in solution in addition to said valuable metals, **characterised** by adding a pH-elevating agent to the leaching solution such as to precipitate the major part of its Fe^{3+} -content and the arsenic present in a first stage; separating the precipitate formed in the first stage from the solution and removing said precipitate from the process; adding a further pH-elevating agent to the solution in a second stage such as to oxidise Fe^{2+} and precipitate the resulting Fe^{3+} and possibly any remaining arsenic; separating the resultant precipitate and any residual solid pH-elevating agent from the solution and returning the same in the process to more acid conditions; and thereafter winning the valuable metal content of the thus purified solution in a manner known per se.
2. A method according to Claim 1, **characterised** by raising the pH to a value within the range of 2.2-2.8 in the first precipitation stage.
3. A method according to Claim 1, **characterised** by raising the pH to a value in the range of 3.0-4.5 in the second precipitation stage.

4. A method according to any one of Claims 1-3, **characterised** in that oxidation is achieved in the second precipitation stage by injecting air into the solution.

5

5. A method according to any one of Claims 1-4, **characterised** by using lime or limestone as the pH-elevating agent.

6. A method according to any one of Claims 1-5, **characterised** by returning solid material separated from the second precipitation stage to the first precipitation stage.

10

7. A method according to any one of Claims 1-6, **characterised** by returning some of the solid material separated from each precipitation stage within respective stages as a nucleating agent.

15

20

25

30


35

40

45

50

55





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 85 0095

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	DD 125 827 A (VEB BERGBAU- UND HÜTTENKOMBINAT "ALBERT FUNK") 18 May 1977 (1977-05-18)	1	C22B19/20 C22B3/44 C22B15/00 C22B23/00
Y	* page 1 - page 5; claims 1-4; figure 1; example 1 *	2-7	
Y	--- DATABASE WPI Section Ch, Week 199252 Derwent Publications Ltd., London, GB; Class M11, AN 1992-426413 XP002147326 & JP 04 318133 A (SUMITOMO METAL MINING CO), 9 November 1992 (1992-11-09) * abstract *	2-7	
Y	--- DE 23 42 729 B (DUISBURGER KUPFERHÜTTE) 30 January 1975 (1975-01-30) * column 3, line 25 - column 5, line 13; claim 1 *	2,4,5	
Y	--- DATABASE WPI Section Ch, Week 199320 Derwent Publications Ltd., London, GB; Class M25, AN 1993-165427 XP002147327 & SU 1 735 404 A (GINTSVETMET RES INST), 23 May 1992 (1992-05-23) * abstract *	3,4	TECHNICAL FIELDS SEARCHED (Int.Cl.7) C22B C25C
Y	--- US 3 510 259 A (EVERETT PETER KENNETH) 5 May 1970 (1970-05-05) * column 4, line 54 - column 5, line 15 *	2-7	
Y	--- US 4 241 039 A (KIBAYASHI TAMOTSU ET AL) 23 December 1980 (1980-12-23) * column 2, line 17 - line 66; claim 1 * * column 4, line 6 - line 53 *	3-5	
	--- -/--		
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 13 September 2000	Examiner Bombeke, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1603 03 82 (P04C01)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 00 85 0095

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
Y	US 3 985 856 A (YANG KANG ET AL) 12 October 1976 (1976-10-12) * column 2, line 56 - column 3, line 5; claims 3,5 *	2,5	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 13 September 2000	Examiner Bombeke, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.92 (P44C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 00 85 0095

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

13-09-2000

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
DD	125827	A	18-05-1977	NONE	
JP	4318133	A	09-11-1992	NONE	
DE	2342729	B	30-01-1975	AT 338004 B	25-07-1977
				AT 569774 A	15-11-1976
				BE 814007 A	16-08-1974
				ES 429518 A	01-09-1976
				FI 179674 A	25-02-1975
				IT 1019086 B	10-11-1977
				NL 7410897 A	26-02-1975
				NO 741691 A	24-03-1975
				SE 7408109 A	25-02-1975
SU	1735404	A	23-05-1992	NONE	
US	3510259	A	05-05-1970	NONE	
US	4241039	A	23-12-1980	JP 1078996 C	25-12-1981
				JP 54082307 A	30-06-1979
				JP 56020338 B	13-05-1981
				AU 519440 B	03-12-1981
				AU 4248278 A	21-06-1979
				BE 872703 A	30-03-1979
				CA 1108376 A	08-09-1981
				DE 2853516 A	28-06-1979
US	3985856	A	12-10-1976	NONE	

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office. No. 12/82